Intertape® 4560



Intertape® 4560 features an absorbent, silk acetate cloth backing with a thermosetting, rubber adhesive. The tape is resistant to impregnating agents, can be printed on directly, and can be torn by hand.

Nominal Values

Backing	Silk Acetate Cloth
Backing Thickness	0,152 mm
Adhesive Type	Natural Rubber, thermosetting
Total Thickness	0,178 mm
Insulation Class	B 130°C
Color	Black, White
Adhesion to Steel	15,00 N/25 mm
Tensile Strength	175,00 N/25 mm
Elongation	15%
Breakdown Voltage (Veff VDE 0303)	2000 V
Insulation Resistance (megaΩ)	$10^4\Omega$
Electrolytic Corrosion	A1,0
Flammability	BU1
UL-File Number	E20790
Length	50 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	4 December 2019

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

Intertape® 4560



Applications

- Coil wrapping
- Tabbing
- Inter-layer insulation

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 08.09.2021

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com